

ALL SEASONS E-Z SAND 3042

Black Waterborne Primer Surfacer for Automotive Bumpers

Urethane Supply Company's ALL SEASONS E-Z SAND is a black, easy-to-sand, freeze-tolerant primer surfacer for plastic bumper refinishing. The high-build formula hides 180 grit sanding scratches and is compatible with all automotive topcoat systems. E-Z SAND dries quickly to a smooth finish that your customers will love. Right out of the can, E-Z SAND offers superior solvent resistance, water resistance and durability.

Benefits:

- Extremely easy to sand.
- E-Z SAND offers outstanding water resistance. If speed dried at 180°F for 20 minutes, E-Z SAND may be wet sanded in one hour. E-Z SAND will not lift if inadvertently exposed to water after it has dried.
- Freeze-Thaw Stable: Passes all quality control tests after 5 freeze-thaw cycles.
- Compatible with all common single-stage and base/clear automotive topcoat systems.
- Outstanding flexibility and adhesion. E-Z SAND does not have the tendency to crack in cold temperatures.

Application:

- Prepare surface by cleaning with 1000 Super Clean, then 1020 Scuff Magic Prep Soap and a red scuff pad.
- Anywhere raw plastic is exposed, spray 1050 Plastic Magic Adhesion Promoter.
- Stir E-Z SAND. Apply a medium wet coat with a base coat gun using a 1.3-1.8 mm nozzle. Ready to spray right out of the can, but may be diluted with water to lower spray viscosity. Orange peel disappears as it dries.
- Allow to dry between coats. E-Z SAND may be top coated at any time after it has completely dried. Dry time varies depending on temperature and humidity; allow at least 60 minutes at 72°F or 20 minutes at 180°F. Sand with 400 to 600 grit sandpaper immediately prior to top coating.
- Clean gun first with water, then with acetone or lacquer thinner. To remove dried paint, use 1030 Eco-Solv.



Customer Support:
 PH: 800-633-3047
 Fax: 800-824-0087
www.urethanesupply.com



**SANDS EASILY!
 DRIES QUICKLY!
 DRIES SMOOTH!**

Dry Time (Varies with Temperature & Humidity)

	Dry Time
Room Temp.	±60 min.
180°F	20 min.

**SCAQMD
 VOC:
 61g/L
 .51 lb/gal**

E-Z SAND Part Numbers

Size	Part Number
Gallon	3042-1
5 Gallon Pail	3042-5
50 Gallon Drum	3042-D

E-Z SAND Specifications

Size	Shipping Weight	Dimensions
Gallon	12.05 lbs.	6.5" dia x 7.5" h
5 Gallon Pail	58.74 lbs	12.8" dia x 15" h
50 Gallon Drum	590.0 lbs	22.5" dia x 36" h

	Product	Recommended
Viscosity Range	24 - 30 sec #3 Zahn Cup	26 sec #3 Zahn Cup
Spray Temperature	50°F - 95°F	72°F
Gun Nozzle Size	1.3 - 1.8 mm	1.3 mm
Dilution with Water	0 - 9%	0 - 4.5%